





# Grabo Acoustic 7

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	3.2
Wear layer thickness	EN ISO 24340	mm	0.7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2.6
<b>CLASSIFICATION</b>			
Product specification	EN 651		✓
European classification	EN 685	class	34/42
Residual indentation	EN ISO 24343	max. mm	0.2
Dimensional stability	EN ISO 23999	max.%	0.2
Light fastness	EN 20105 B02	grade	6
<b>PERFORMANCE</b>			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Bfl-s1
	BS 476		Class 1
	Gost 30402-94		G1
Impact sound reduction	EN ISO 140-8	DL <sub>w</sub> (dB)	19
Slip resistance	DIN 51130		R9
Electrical resistance	EN 1815	kV	< 2
	EN 1081	Ω	≤ 10 <sup>9</sup>
Chemical resistance	EN ISO 26987		✓
Bacterial resistance	EN ISO846:1999		✓
Castor chair resistance	EN ISO 4918		✓
Surface treatment			CLP
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes		 	Phthalate-, Solvent and Heavy metal free product
Seaming method			heat or cold weld
<b>CE MARKING</b>	<b>EN 14041</b>		✓